

Densifier RBP



DESCRIPTION

A Lithium-based metallic stain for concrete and masonry.

COVERAGE / TREATMENT YIELD* sq ft per gallon:

Wire Cut Brick	200-300
Rough Brick	150-300
Split Face Block	200-300
Smooth SCC Concrete	300-500

APPLICATION

- Coverage rate will vary with concrete quality and finish

RECOMMENDED FOR

- Brick
- Concrete
- Concrete Block
- Precast Panels
- Tilt Up Construction

DRYING TIME

1-2 hours

PHYSICAL PROPERTIES

- Form viscous liquid, color matches label
- Total Solids 26-30 % Specific Gravity: 1.15 – 1.17
- pH 11
- Film yes
- Flash Point: None
- V.O.C. Content Less than 50 g/L
- Freeze point 32° F (0° C)
- Abrasion Resistance excellent
- Depth of Surface Penetration 2-8mm (non pigment chemistry)
- Shelf Life 6 months in factory sealed container

